USSN: 10/533,410

## Claim Amendments

3204-01

What is claimed is:

- 1. (Currently Amended) A method for providing a resinous coating material on glass exhibiting improved adhesion thereto, comprising
  - (a) supplying to said glass a coating composition comprising
    - (i) a reactive sulfonic acid derived compound; and
    - (ii) a resinous coating material

wherein said reactive sulfonic acid derived compound contains an olefinic double bond capable of reaction.

## 2. (Canceled)

- 3. (Original) The method of claim 1 wherein said reactive sulfonic acid derived compound has a number average molecular weight of less than about 700.
- 4. (Original) The method of claim 1 wherein said reactive sulfonic acid derived compound is an unsaturated-hydrocarbylamido-alkanesulfonic acid or a salt thereof.
- 5. (Original) The method of claim 4 wherein said unsaturated-hydrocarbylamido-alkanesulfonic acid or salt thereof is 2-acrylamido-2-methylpropanesulfonic acid or a salt thereof.
- 6. (Original) The method of claim 1 wherein said reactive sulfonic acid derived compound (i) and said resinous coating material (ii) are each dissolved or dispersed in (iii) a liquid carrier.
- 7. (Original) The method of claim 6 wherein the liquid carrier is an aqueous liquid carrier and wherein at least a portion of said aqueous liquid carrier is subsequently removed.
- 8. (**Original**) The method of claim 7 wherein the removal of said aqueous liquid carrier comprises drying.
- 9. (Original) The method of claim 1 wherein the resinous coating material comprises a urea-formaldehyde resin, a phenol formaldehyde resin, a melamine formaldehyde resin, a polyvinylacetate resin, a polyvinylalcohol resin, an acrylic or methacrylic resin, an epoxy resin, or mixtures thereof.
- 10. (Original) The method of claim 1 wherein the glass is in the form of glass fibers, a fiberglass mat, plate glass, or a glass article.

USSN: 10/533,410

11. (Original) The method of claim 1 wherein the coating composition is applied to the glass by spraying, dipping, brushing, rolling, curtain coating, powder coating, or extrusion.

- 12. (Original) The method of claim 1 wherein the reactive sulfonic acid derived compound and the film forming resin are present in relative amounts of about 0.1:99.9 to about 50:50 by weight.
- 13. (Original) A method for imparting improved adhesion of a resinous coating material to glass, comprising:
- (a) coating the glass with a first coating composition comprising a reactive sulfonic acid derived compound; and
  - (b) applying, to said coated glass, a resinous coating material.
- 14. (Original) The method of claim 13 wherein said resinous coating is applied from a solution or dispersion.
  - 15. (Original) A glass composition comprising:
  - (a) a glass substrate and
  - (b) a coating, comprising
    - (i) a reactive sulfonic acid derived compound; and
    - (ii) a resinous coating material.
- 16. (Original) The glass composition of claim 15 wherein the glass substrate is in the form of glass fibers, a fiberglass mat, plate glass, or a glass article.
- 17. (Original) The glass composition of claim 15 wherein the reactive sulfonic acid derived compound is an unsaturated-hydrocarbylamido-alkanesulfonic acid or a salt thereof.
- 18. (Original) The glass composition of claim 17 wherein the unsaturated-hydrocarbylamide-alkanesulfonic acid or salt thereof is 2-acrylamido-2-methylpropanesulfonic acid or a salt thereof.
- 19. (Original) The glass composition of claim 15 wherein the film-forming resin comprises urea-formaldehyde resin, a phenol formaldehyde resin, a melamine formaldehyde resin, a polyvinylacetate resin, a polyvinylalcohol resin, an acrylic or methacrylic resin, an epoxy resins, or mixtures thereof.
- 20. (Original) The glass composition of claim 15 wherein the reactive sulfonic acid derived compound and the film forming resin are present in relative amounts of about 0.1:99.9 to about 50:50 by weight.
  - 21. (Original) A glass composition comprising:

USSN: 10/533,410

- (a) a glass substrate with
- (b) a coating comprising a reactive sulfonic acid derived compound; said glass composition exhibiting improved adhesion ability to a resinous coating material that may be additionally applied.
- 22. (Original) The glass composition of claim 21 further comprising (c) a coating of a resinous coating material.